

# Transverse Sound Revisited: A Directional Probe of the A-Phase of $UPt_3$

Brett Ellman and Louis Taillefer

*Department of Physics, McGill University, 3600 University Street, Montréal, Québec, Canada  
H3A 2T8*

Mario Poirier

*Centre de Recherche en Physique du Solide, Département de Physique, Université de Sherbrooke,  
Sherbrooke, Québec, Canada J1K 2R1*

(February 1, 2008)

## Abstract

We have measured the transverse ultrasonic attenuation,  $\alpha_{q\epsilon}$ , in a well-characterized single crystal of  $UPt_3$  for propagation direction,  $\mathbf{q}$ , in the basal plane and polarization,  $\epsilon$ , in and out of the plane. Unlike previous measurements, the sample was of sufficient purity to exhibit three well-defined phases as a function of temperature and magnetic field. We uncover a functional dependence for the attenuation in the (zero field) high temperature phase (A-phase) which is distinctly different than that in the low temperature (B) phase. Our data provide unique directional information on the quasiparticle momentum distribution in this largely unstudied phase of  $UPt_3$  and provide the first direct evidence that the two zero-field phases possess different symmetries.

PACS numbers 74.25.Ld, 74.70.Tx

Typeset using REVTeX

Following the discovery of multiple superconducting phases in  $UPt_3$  [1] numerous theoretical investigations have attempted to predict the gap structure in each of the three phases. These calculations have been very successful in predicting measured phase diagrams obtained under magnetic field, hydrostatic pressure, and uniaxial stress. Indeed, the theoretical H-T-P phase diagram agrees with that that observed under every experimental scenario investigated to date [2,3]. While many experiments agree as to the location of the phase lines, it is notable that there are very few direct measures of the *gap structure* within each phase. Here, "direct" means an experimental probe that couples to the quasiparticle density in such a way that the quasiparticle momentum distribution may be mapped. Potential examples include thermal conductivity [4], ultrasound attenuation [5], muon spin resonance [6], and point contact spectroscopy [7], each of which has yielded insights into the gap structure of the low temperature (B) phase. Studies of the high temperature (A) phase have been very limited, however, largely due to the very small temperature range (about 60 mK) over which the A-phase exists. Thus thermal conductivity data, which have strongly constrained parameter space for the B-phase, are insufficiently sensitive to the growth of the gap near  $T_c$  to similarly address the properties of the A-phase. Point contact spectroscopy, while an elegant probe of the gap structure, is similarly limited since the exact temperature of the A/B phase transition was not known for the samples used. Considering the small temperature region over which the A-phase may be studied, it is essential to perform experiments on independently characterized samples using an experimental probe which is sensitive to the onset of superconductivity. The data presented here satisfy these criteria and constitute the most definitive evidence for a different gap symmetry in the A vs. the B-phase.

Transverse ultrasonic attenuation is one of the most powerful tools for investigating the geometric properties of the superconducting gap. The strengths of transverse sound attenuation,  $\alpha_{q\epsilon}(T)$ , lie in its strong dependence on the magnitude of the gap and also on its highly directional nature involving two independent vectors, the propagation direction,  $\mathbf{q}$ , and the polarization,  $\epsilon$ . Ultrasonic attenuation changes very sharply on entering the super-

conducting state. The relative sensitivity of sound attenuation as compared to, for example, the thermal conductivity,  $\kappa$ , may be motivated by considering the energy dependence of the integrand of the appropriate BCS quantities:

$$\kappa \sim \int_{\Delta(T)}^{\infty} E^2 \frac{\partial f}{\partial E} dE \quad (1)$$

$$\alpha \sim \int_{\Delta(T)}^{\infty} \frac{\partial f}{\partial E} dE \quad (2)$$

Both  $\alpha$  and  $\kappa$  depend on the number of quasiparticles per unit energy and thus on the derivative of the Fermi function,  $\partial f/\partial E$ . However, the expression for  $\kappa$  has an energy prefactor  $E^2$  because thermal conductivity depends on energy transport. Since  $\partial f/\partial E$  is peaked at  $E = 0$ , as the gap  $\Delta(T)$  becomes non-zero the energies contributing the most to the  $\alpha$  integral are excluded and the attenuation drops sharply (as  $\alpha(T) = 2f[\Delta(T)]$ ). The integrand of  $\kappa$ , however, is zero at  $E = 0$  and thus the thermal conductivity is a much weaker function of  $\Delta$  near  $T_c$ .

Transverse sound attenuation is also very sensitive to gap anisotropy. Indeed, it was transverse attenuation data that first provided definitive evidence for a highly anisotropic gap in  $UPt_3$  [5]. These measurements found a linear dependence of the attenuation for  $\alpha_{ab}$  ( $\epsilon||\hat{b}$  and  $\mathbf{q}||\hat{a}$ ) while  $\alpha_{ac} \sim T^3$ . Thus the measured attenuation was not only decidedly non-BCS ( $\alpha_{ij} \sim \exp(-\Delta/T)$  for all i,j at low T) but also manifestly anisotropic. In the "dirty limit" (see below) appropriate to all experiments to date, the analysis of Kadanoff and Falko [8], later extended to the resonant impurity case by several groups [9], gives for the attenuation (outside of any gapless regime near  $T = 0$ )

$$\alpha_{q\epsilon} \propto \int_0^{\infty} d\omega \frac{\partial f(\omega)}{\partial \omega} \frac{1}{\text{Im}(\Sigma_0)} \left\langle \frac{p_{\epsilon}^2 p_q^2 \sqrt{\omega^2 - \Delta(p)^2}}{\omega} \right\rangle_p, \quad (3)$$

where  $\Sigma_0(\omega, T)$  is the electronic self-energy (independent of polarization or propagation direction),  $\Delta(p)$  is the gap,  $p_{\epsilon}$ ,  $p_q$  are the projections of momentum,  $p$ , along the appropriate directions on the Fermi surface, and  $\langle \rangle_p$  is an average over the Fermi surface restricted so that  $\omega^2 - \Delta(p)^2 > 0$ . The function  $\Sigma_0$  includes the effects of resonant impurity scattering [10] which modify the energy-dependent electronic mean free path. The point is that the

experimental parameters  $q, \epsilon$  act solely as weights in the Fermi surface average of a function of  $\Delta_p$ . Therefore, in principle, the transverse attenuation allows one to directly map out the k-space location of nodes. As an example, we consider the effect on  $\alpha_{ac}$  of a line node in the hexagonal basal plane of  $UPt_3$  (e.g.,  $\Delta(k_c = 0) = 0$ ). The product of momenta  $p_q p_\epsilon$  in Eq. 3 is then equal to  $p_a p_c$ , which vanishes in the basal plane. Thus the contribution of a line node to the attenuation  $\alpha_{ac}$  is much reduced as compared to its contribution to  $\alpha_{ab}$ . That this is in qualitative agreement with the results of Ref. [5] constitutes strong evidence that there is a basal plane line node in the B-phase of  $UPt_3$ . The *relative* sizes of the  $\alpha_{ij}$  for various model gaps may all be qualitatively explained in like manner. However, a caveat is essential: the functional form of  $\alpha(T)$  may depend strongly on the form of  $\Delta_p$  far from the node, even at relatively low temperatures. Thus only a careful, self-consistent calculation can be confidently compared with experimental data. Detailed calculations [9] based on Eq. 1 found the aforementioned experimental results [5] to be in qualitative agreement with a gap having a line node in the basal plane. These data, however, do not bear on the question of the gap structures of the multiple phases in  $UPt_3$  insofar as the sample used predated the growth of high-purity, low strain crystals exhibiting the now familiar phase diagram. We have performed transverse sound attenuation studies on a single crystal of  $UPt_3$  which is known to support three superconducting phases in the temperature-field plane. Most notably, our data are unique in providing an incisive directional probe of the gap structure in the high-T/low field A-phase.

The sample used was a single crystal rectangular prism approximately  $1 \times 1 \times 2.7 \text{ mm}^3$  in size. The sound was propagated along the long dimension which in turn corresponds to the crystallographic a-axis. Ultrasound was generated using 30 MHz lithium niobate transducers. The attenuation was measured using a conventional pulse-echo interferometer in a transmission geometry at frequencies ranging from 90 - 290 MHz. The frequency dependence of the attenuation was as expected for a metal, a point which will be considered in more detail below. The sample is the same one used by Adenwalla *et al.* [11] in their careful study of the phase boundaries using longitudinal sound velocity measurements. We

therefore know to high precision the location of the phase boundaries *a priori*, an important advantage when studying the functional form of the attenuation over the small temperature range covered by the A-phase. The  $T_c$ 's obtained from our data are in excellent agreement with those obtained in Ref. [11]:  $T_c^+ = 495\text{mK}$  and  $T_c^- = 435\text{ mK}$ .

The measured attenuation for polarization in and transverse to the hexagonal basal plane are shown in Figs. 1 and 2, respectively. The normal state attenuation is a decreasing function of temperature, which is a consequence of the fact that the electrical conductivity also falls with increasing temperature. (For a Fermi liquid in the dirty limit [13],  $\alpha(T) \propto \sigma(T)$ .) The experimental technique determines  $\alpha(T)$  up to an additive constant corresponding to sound loss in cables, bonding layers, and so forth. We fix this parameter by demanding that  $\alpha(T = 0) = 0$ . It is important to realize that there is no thermodynamic reason that this condition must hold. Indeed, some pertinent theories predict a non-zero attenuation at zero temperature. Therefore this experiment (or any similar work of which we are aware) cannot directly address the issue of a residual attenuation at  $T=0$  reflecting a finite density of zero energy excitations. (This question is addressed by recent thermal conductivity results [4]). Independent of any theoretical interpretation, it is evident that our B-phase results (i.e.,  $T < 440\text{ mK}$ ) are in agreement with those of Ref. [5]:  $\alpha_{ab} \sim T$  and  $\alpha_{ac} \sim T^n$  with  $n \sim 3$ . The exact power law dependence of the attenuation should not be taken too seriously, particularly for  $\alpha_{ac}$ . We also note that the absolute magnitudes of our data are in general agreement with Ref. [5] after appropriate frequency normalization, as discussed below.

The main results of this work are the sharp differences observed in the attenuation of the A-phase ( $500\text{ mK} > T > 440\text{ mK}$ ) as compared to the B-phase. As may be seen in Fig. 3,  $\alpha_{ab}$  drops quickly with decreasing  $T$  before becoming essentially constant, while  $\alpha_{ac}$  has a "bump" seemingly superimposed on the sharply falling attenuation observed in the B-phase. Interestingly, the data of Fig. 3 show that  $\alpha(T)$  attains its low temperature asymptotic functional form for phase B within a small range  $\Delta T \leq 25\text{ mK}$  below  $T_c^-$ . Making an analogous assumption about the normal-state/A-phase transition, it is tempting to assume that the

essentially constant  $\alpha(T)$  seen in Fig. 3 may be used to predict the gap structure of the A-phase without worrying about the small temperature range available. Quite aside from any other objections, however, such an assumption neglects the effect of superconductivity on the quasiparticle-quasiparticle scattering in  $UPt_3$ . Above  $T_c$ , quasiparticle-quasiparticle interactions lead to a conductivity  $\sigma(T) = 1/(\rho_0 + AT^2)$  where, the elastic and inelastic contributions are the same order of magnitude at  $T_c$ . On entering the superconducting state, the quasiparticle density falls, leading to a decrease in the inelastic term, presumably within a fairly small temperature interval below  $T_c$ . The corresponding increase in the quasiparticle mean free path would then lead to an increase in  $\alpha$  with decreasing T. Quantitative interpretations of the A-phase data assuming a specific gap must carefully consider this effect, particularly since the structure and evolution of the gap at high temperatures affect the quasiparticle density and therefore the magnitude of the inelastic scattering. We emphasize, however, that while changes in inelastic scattering due to superconductivity might affect the *size* of the observed anisotropy, they are not expected to *give rise* to anisotropy which otherwise would not be present.

Qualitatively, our data allow us to immediately conclude that more quasiparticles exist in the A-phase than would be present if the B-phase extended up to the same temperature. Furthermore, it appears that these extra excitations preferentially scatter sound when the polarization is in the basal plane. To see this we plot, in Fig. 4, the data of Figs. 1 and 2 normalized to the attenuation at either  $T_c^+$  or  $T_c^-$  as a function of temperature normalized to the appropriate critical temperature. This allows us to compare, say, the B-phase attenuation (for either polarization) with the attenuation in the A-phase over the same reduced temperature range. It is evident that  $\alpha_{ab}$  is much enhanced in the A-phase as compared to the B-phase. The data for the c-axis polarization,  $\alpha_{ac}$ , however, are roughly equal in the two phases. The latter result implies that there is either a serendipitous combination of inelastic scattering effects and quasiparticle contributions far from the gap that lead to the similarity of the A and B-phase results, or that the gap structures in the two cases possess the same nodal weight in the a-c plane. (According to Eq. 3, this plane contributes most strongly to

the attenuation.) The latter explanation is puzzling in the context of popular theories [3] (such as the  $E_{1g}$  scenario mentioned in the discussion of the B-phase results) that predict a line node perpendicular to the basal plane in the A-phase, with the orientation of the nodal plane determined by the direction of the antiferromagnetic order parameter. The latter is known to form many small domains in the sample along the three  $a^*$  (k-space) directions. Therefore, regions of the sample would possess a line node which is not perpendicular to either  $\epsilon||c$  or  $q||a$ . According to Eq. 3, such nodes would contribute more quasiparticles with favorable momenta than the c-axis point nodes that are postulated to exist in the B-phase, leading to an enhanced attenuation in the A-phase. Such speculations, of course, emphasize the need for a complete theoretical treatment.

The data of Fig. 3 contain precise information on the momentum space distributions of quasiparticles, and thus on the gap structure. As mentioned above, such detailed information can only be extracted by comparison with complete calculations analogous to the published B-phase computations taking proper account of inelastic scattering. In the absence of pertinent theoretical predictions, we conclude with some strictly qualitative observations on sample dependence. The effect of anisotropy in the quasiparticle spectrum on the attenuation critically depends on the measurement frequency and the purity of the sample. In the clean limit, defined as  $ql \gg 1$ , where  $l$  is the electronic mean free path and  $q$  the phonon wavevector, energy-momentum conservation implies that only quasiparticles with momenta very nearly perpendicular to  $q$  may contribute to the attenuation. Though somewhat analogous to the effect of the  $p_\epsilon p_q$  term in Eq. 1, the clean limit attenuation is affected by a much smaller region of the Fermi surface. In this limit, therefore, attenuation is a very effective probe of the anisotropy of both the Fermi surface and the gap in a superconductor. In fact, attenuation data in this regime was one of the most effective early techniques used in studies of the anisotropic gaps found in conventional superconductors [12]. We have measured the frequency dependence of the normal state attenuation in our sample and find approximate  $\omega^2$  scaling, as predicted for the hydrodynamic regime. Deviations from perfect scaling [13] indicate, however, that  $ql$  may be as large as 0.2 at the top of

our frequency range (about 300 MHz). We may therefore roughly estimate the quasiparticle mean free path in the normal state as  $l \approx 300$  nm. This is in accord with estimates of the mean free path from, e.g., de Haas-van Alphen experiments [14]. Cleaner samples and/or higher frequencies may thus make the clean regime accessible in the near future.

In conclusion, we have measured the attenuation of transverse ultrasound in the A and B phases of  $UPt_3$ . Our B-phase data are in agreement with published results [5]. The A-phase data are qualitatively different and display a significant directionally-dependent enhanced density of quasiparticles as compared to the B-phase. In combination with resonant impurity scattering calculations which take into account the normal state properties, these data should provide some of the first constraints on the symmetry of the A-phase.

#### Acknowledgments

We would like to thank Andreas Fledderjohann for very useful conversations and the use of his results before publication and Mario Castonguay for technical assistance. This work was supported by grants from the Fonds pour la Formation des Chercheurs et l'Aide à la Recherche of the Government of Québec and from the Natural Science and Engineering Research Council of Canada. L.T. acknowledges the support of the Canadian Institute for Advanced Research and the A.P. Sloan Foundation.



## REFERENCES

- [1] R.A. Fisher *et al.*, Phys. Rev. Lett. **62**, 1411 (1989); K. Hasselbach, L. Taillefer, and J. Flouquet, Phys. Rev. Lett **63**, 93 (1989); L. Taillefer, Hyp. Int. **85**, 379 (1994).
- [2] For example, K.A. Park and R. Joynt, preprint.
- [3] For a review of various theories, see R. Joynt, J. Magn. Magn. Mater. **108**, 31 (1992).
- [4] B. Lussier, B. Ellman, and L. Taillefer, Phys. Rev. Lett. **73**, 3294 (1994); B. Lussier, B. Ellman, L. Taillefer, preprint.
- [5] B.S. Shivaram *et al.*, Phys. Rev. Lett. **56**, 1078 (1986).
- [6] C. Broholm *et al.*, Phys. Rev. Lett. **65**, 2062 (1990).
- [7] H. Von Lohneysen and G. Goll, J. Low Temp. Phys **95**, 199 (1994); Y. De Wilde *et al.*, Phys. Rev. Lett. **72**, 2278 (1994); G. Goll *et al.*, Phys. Rev. Lett. **70**, 2008 (1993).
- [8] L.P. Kadanoff and I.I. Falko, Phys. Rev. **136**, A1170 (1964).
- [9] P. Hirschfeld, D. Vollhardt, and P. Wölfe, Solid State Commun. **59**, 111 (1986); B. Arfi, H. Bahlouli, and C.J. Pethick, Phys. Rev. B **39**, 8959 (1989); A. Fledderjohann, unpublished
- [10] C.J. Pethick and D. Pines, Phys. Rev. Lett. **57**, 118 (1986).
- [11] S. Adenwalla *et al.*, Phys. Rev. Lett. **65**, 2298 (1990).
- [12] R.W. Morse, T. Olsen, and J.D. Gavenda, Phys. Rev. Lett. **3**, 15 (1959).
- [13] A.B. Pippard, Phil. Mag. **46**, 1104 (1955).
- [14] L. Taillefer et al., J. Magn. Magn. Mat. **63 & 64**, 372 (1987).

## FIGURES

FIG. 1. Transverse ultrasonic attenuation,  $\alpha_{ab}$ , for propagation along  $\hat{a}$  and polarization along  $\hat{b}$ . The low temperature attenuation shows no curvature down to 130 mK.

FIG. 2. Transverse ultrasonic attenuation,  $\alpha_{ac}$ , for propagation along  $\hat{a}$  and polarization along  $\hat{c}$ . The attenuation drops much more quickly than  $\alpha_{ab}$ , reflecting the insensitivity of  $\alpha_{ac}$  to quasi-particles in the basal plane.

FIG. 3. (a) Detail of  $\alpha_{ab}$  in the A-phase. After a drop at  $T_c$ , the attenuation reaches a plateau before dropping sharply on entering the B-phase. This behavior reflects a larger quasiparticle density in the A than in the B-phase. The arrows designate  $T_c^-$  and  $T_c^+$  as determined from longitudinal sound velocity data[10]. (b) Detail of  $\alpha_{ac}$  in the A-phase. The onset of the B-phase is evident as a small "bump" near  $T_c^- = 435$  mK.

FIG. 4. Transverse attenuation data for both polarizations normalized to the value of the attenuation at  $T_c^+$  and  $T_c^-$  as a function of  $T/T_c^{+,-}$ . This choice of normalization allows us to compare the attenuation in the A and B phases over the same (reduced) temperature range. The A-phase shows an enhanced in-plane attenuation vs. the B-phase while the out-of-plane polarization data are roughly equal in the two phases. The lines are guides to the eye.







